

Application Serial No. 10/825,450

AMENDMENT TO THE SPECIFICATION

Please replace the pending paragraph 74 with the following:

[0074] An adhesive interface layer 4 was then extrusion coated by applying to the hole blocking layer, a wet coating containing 5 percent by weight based on the total weight of the solution of polyester adhesive (~~Mer-Ester~~ MOR-ESTER 49,000, available from Morton International, Inc.) in a 70:30 volume ratio mixture of tetrahydrofuran/cyclohexanone. The resulting adhesive interface layer 4, after passing through an oven, had a dry thickness of 0.095 micrometer.